

## **Art 522 PRIMER**

Primer paint for painting iron

---

### **GENERAL SPECIFICATIONS:**

Antirust with oil base and iron oxide pigments, which ensure a good bond to the entire surface of the painted metal and long resistance to time.

---

### **ADVICE:**

- It is used in ventilated rooms
  - Do not use on hot surfaces or in direct sunlight
  - After use, work tools should be cleaned with nitro thinner
  - Store the product in dry places and away from contact with the sun and heat sources
  - Do not throw waste in open areas
- 

### **APPLICATION DETAILS:**

The new surface The surface is cleaned from rust with a wire brush with paper or with a machine according to the required standard and then with a wet cloth and with oil thinner it is passed over the entire surface to remove dust, after drying the surface is passed with a brush hand with Art 522 and at least after 12 hours it is applied with the second coat. After another 12-24 hours it is applied with the selected enamel paint. moistened with oil, it is passed over the entire surface to remove dust. After the surface is dry, one hand is passed with a brush with Art 522 and at least after 12 hours, the second hand is passed. After another 12-24 hours, it is passed with the selected enamel paint

---

## CHARACTERISTICS:

<b>Binder:</b>	With oily resins
<b>Visual aspect:</b>	thick gray, red, white, black liquid
<b>Drying (at temp. 20°):</b>	surface 2 hours
<b>Complete:</b>	24-36 hours Second coat after 24 hours
<b>Dilution:</b>	Ready to use
<b>Use:</b>	Brush, roller, spray
<b>Consumption:</b>	8-12 m <sup>2</sup> /lt with one hand
<b>Confection:</b>	5kg, 25kg

---

All the above technical data are the fruit of our experience, they have a guiding character for the final result. The data in the technical tab can be changed based on possible changes in raw materials and production technology. Before using the product, we always advise that a preliminary test is done with the product\*

---